



Sơn Nippon
Sơn Đẹp Cũng Đẹp

Ref. No. : PDS-0705-EN

Version No. : 3

Update Date :13.09.18

PRODUCT DATA SHEET

PYLAC 3000

Product Description:

Nippon Paint PYLAC 3000 is an acrylic modified alkyd nitro-cellulose paint that is specially formulated for decorative and protective purposes. It is suitable for both exterior and interior applications. It can be used on metal, timber and paper surfaces. It can be cured extremely fast at low temperature and provides good adhesion on various surfaces.

Physical Characteristics of Paint:

Colour	: Full range of colours as request
Finish	: Gloss
Specific Gravity	: 1.08 ± 0.05 ⁽¹⁾
Solid Content	: 25 ± 2 by volume ⁽¹⁾

Remark: (1) Base on White colour

Performance Characteristics:

- Durable, washable & quickly-drying at low temperature
- Good adhesion & superior gloss & colour retention
- Good film properties such as hardness & flexibility
- Excellent colour uniformity
- Wide selection of bright and attractive colours
- Convenient and easy application by spraying

Recommendation for Use:

Surface Preparation

The surface to be painted must be dry, clean and free from dirt, grease, oil and other contaminations. Method of surface preparation depends on the type of substrate and the condition under which it will operate.

Ferrous Metal - Prime with NIPPON 1100 FAST DRYING PRIMER for better result.

Non-Ferrous Metal - Prime with NIPPON VINILEX 120 ACTIVE PRIMER

Wood and Timber - Prime with BILAC ALUMINIUM WOOD PRIMER

Recommended No. of Coats : 1 - 2 coats

Recommended Film Thickness per coat : 30 microns for dry film
122 microns for wet film

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam
Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

www.nipponpaint.com

PYLAC 3000

Theoretical Coverage at Recommended Film Thickness : 8.2 m² / liter (for dry film thickness of 30 microns)

$$\text{Theoretical Coverage (m}^2/\text{liter)} = \frac{\text{Volume Solid (\%)} \times 10}{\text{Dry Film Thickness (\mu)}}$$

Practical Coverage (20% Loss Factor) : 6.6 m² / liter (for dry film thickness of 30 microns)

Note : This theoretical coverage rate has been calculated from the volume solid of the material and is related to the amount of coating applied onto a perfectly smooth surface without wastage. For a practical coverage rate, due allowance should be made for atmospheric conditions, surface roughness, geometry of the article being coated, the skill of applicator, method of application etc. when estimating quantities required for a particular job.

Application Data:

Application Methods : Brush, roller, compressed air spray and airless spray

Guiding Data for Spray	:	<u>Air</u>	<u>Airless</u>
		Delivery Pressure (kg/cm ²)	3 - 4
		Tip size at 60° angle	1.3 mm
			0.015"-0.017"

Thinning	:	Roller & Brush	10% maximum
		Air Spray	20% maximum
		Airless Spray	5% maximum

Thinner : PYLAC 3500 THINNER

Cleaning Solvent : PYLAC 3500 THINNER

Note: All equipment should be cleaned IMMEDIATELY with Thinner after use. For thinning, substitute thinners other than those approved or supplied by Nippon Paint may adversely affect the product performance and void product warranty whether expressed or implied.

Drying Time at 25°C to 30°C:

Dry to touch	:	Approximately 3-5 minutes
Dry to handle	:	1 hours
Dry to overcoat	:	Minimum 3 hours

Standard Packing : 1 Liter & 5 Liters

Environmental Conditions during Application:

1. Do not apply when the relative humidity exceeds 85%. The temperature of the substrate to be painted must be 3°C higher than the dew point.
2. Do not apply at temperature below 7°C. If not, drying and overcoating time will be considerably extended.

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam
Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

www.nipponpaint.com

PYLAC 3000

3. During application of the paint, naked flame, welding operations and smoking should not be allowed and good ventilation is necessary.

Safety, Health and Environmental Information:

1. Flammable Liquid. Do not expose to heat, sparks or open flame.
2. Skin Contact: May cause moderate skin irritation. Avoid prolong contact with skin. Use solvent resistant glove. To remove splashes of paint from skin, use soap and water.
3. Inhalation: Respiratory irritation. Only used in well ventilated areas. Do not breathe vapor or spray paint. Respirator with organic vapor cartridges recommended.
4. Eye Contact: Cause severe eye irritation and blurred vision. Safety glasses / goggles with side shields recommended. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
5. Ingestion: Harmful if swallowed. Keep away from drinks, food and out of reach of children. If swallowed, seek medical advice immediately and show the container or label.
6. In the event of an accident, contain and collect spillage using sand or earth or absorbent. Do not empty into drain or water courses.
7. Wastes and empty containers should be treated and disposed of in accordance with national and local regulations. Empty containers and packaging should be taken for recycling, recovery or disposal through a suitably qualified or licensed contractor.

NOTE: The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for specific application, please contact Nippon Paint Sales & Marketing Dept. We reserve the right to modify our product data sheet without further notice.

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam
Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

 www.nipponpaint.com